

Caratteristiche tecniche

· Tile Performance Data · Caracteristique Technique · Technische Daten · Техническая Характеристика

Classificazione secondo EN 14411 ISO 13006 annesso G gruppo Bla con Ev ≤0,5 % - Classification in accordance with EN 14411 ISO 13006 annex G standards Bla with Ev ≤ 0,5% - Classification selon EN 14411 ISO 13006 annexe G groupe Bla avec Ev ≤0,5% - Klassifizierung gemäß EN 14411 ISO 13006 anlage G Gruppe Bla mit Ev ≤0,5% - Классификация в соответствии с EN 14411 ISO 13006, приложение G, стандарт Bla, где Ev ≤0,5%

Caratteristica Tecnica Tile Performance Data Caracteristique Technique Technische Daten Техническая Характеристика		Metodo di prova Tests method Methode d'essai Testmethode Метод испытания		Valore * Medio "Caesar" - Average "Caesar" Value * - Valeur * Moyen "Caesar" "Caesar" Durchschnittswert * - Среднее Значение "Caesar" *						
				AEXTRA20						
	Dimensione - Size Dimension - Abmessungen - Размер	ISO 10545-2	Conforme - In accordance Conforme - Erfüllt - Соответствует							
	Assorbimento d'acqua* - Water absorption* Absorption d'eau* - Wasseraufnahme* - % Поглощения воды*	ISO 10545-3	≤ 0,1%							
	Resistenza alla flessione* - Bending strength* Résistance à la flexion* - Biegezugfestigkeit* Упругость*	ISO 10545-4	Non applicabile a piastrelle con una forza di rottura Not applicable to tiles with a breaking strenght N'est pas applicable aux carreaux avec une charge de rupture Nicht anwendbar bei Fliesen mit einer Bruchlast Не применяется в отношении плиток с прочностью на разрыв ≥ 3000 N							
	Sforzo di rottura (S) - Breaking strength Charge de rupture - Bruchlast - Ударопрочность	ISO 10545-4	> 10.000 N							
	Resistenza all'abrasione profonda* - Deep scratch resistance* Résistance à l'abrasion profonde* - Widerstand gegen Tiefenverschleiß* - Устойчивость глубокому истиранию*	ISO 10545-6	Conforme - In accordance Conforme - Erfüllt - Соответствует							
	Coefficiente di dilatazione termica lineare* Thermal linear expansion coefficient* Coefficient de dilatation thermique linéaire* Koeffizient der linearen thermischen Dehnung* Коэффициент линейного теплового расширения*	ISO 10545-8	≈ 7 (10 ⁻⁶ °C ⁻¹)							
	Resistenza agli sbalzi termici* - Termal shock resistance* Résistance aux écarts de température* - Temperaturwechsel Beständigkeit* - Устойчивость к тепловому перепаду*	ISO 10545-9	Resistente - Resistant Résistante - Beständig - Стойкий							
	Dilatazione all'umidità* - Expansion in humidity* Dilatation à l'umidité* - Feuchtigkeitsausdehnung* Расширение в условиях влажности*	ISO 10545-10	≤ 0,1 (mm/m)							
	Resistenza al gelo* - Frost resistance* Résistance au gel* - Frostbeständigkeit* Морозоустойчивость*	ISO 10545-12	Resistente - Resistant Résistante - Beständig - Стойкий							
	Resistenza all'attacco chimico* - Resistance to chemical attack* Résistance à l'attaque chimique* - Beständigkeit gegen Chemikalien* - Устойчивость к химическому воздействию*	ISO 10545-13	Resistente - Resistant Résistante - Beständig - Стойкий							
	Carico statico - Static load Charge statique - Statische Last Статическая нагрузка	EN 12825	Centro - Centre Au centre - Mitte - По центру Centro lato - Side centre Au centre latéralement - Mitte Seite - По центру грани Diagonale - Diagonal En diagonale - Diagonal - По диагонали	45x90 KN>5,0	60x60 KN>7,0	60x90 KN>8,0	80x80 KN>7,0	60x120 KN>5,0	30x120 KN>3,0	
	Classe di carico di rottura*** - Breaking load class*** Classe de charge de rupture*** - Bruchlastklasse*** Класс стойкости к разрушающей нагрузке***	EN 1339	U11 T11							
	Resistenza alle macchie* - Resistance to stains* Résistance aux taches* - Fleckenbest ndigkeit* Устойчивость к образованию пятен*	ISO 10545-14	Pulibile - Cleanable Nettoyable - Leicht zu reinigen - Чистящийся							
	Resistenza allo scivolamento** - Slip resistance** Résistance au glissement** - Rutshemmende Eigenschaft** Сопротивление скольжению**	EN 16165-B EN 16165-A	R11 B: Yard, Sidewalk R11 C: Other colours							
		▲ ANSI A326.3	WET DCOF ≥0,55							
	Spessore nominale - Nominal Thickness Epaisseur nominal - Nominalstärke Номинальная толщина		20 mm							

* Valori medi riferiti agli ultimi due anni di produzione. Averege values referred to the lasto two years of production. Valeurs moyennes des deux denrnières années de production. Durchschnittswerte, die sich auf die letzten zwei Productionsjahre beziehen. Средние значения относятся к последним двум годам производства и натуральной отделке поверхности.

** Valori relativi alla finitura naturale del prodotto ed a test effettuati da laboratori esterni accreditati, disponibili in azienda; ci rendiamo disponibili alla verifica dell'eventuale lotto interessato all'acquisto. As far as values relating to the matt finish of the product and to tests carried out by certified external laboratories whose results are available upon request at Headoffice, we are willing to check the lot you are interested in purchasing. Valeurs se référant à la finition naturelle du produit selon des tests effectués par des laboratoires extérieurs accrédités et à la disposition de toute personne intéressée auprès de nos bureaux; nous sommes disponibles puor le contrôle de l'éventuel lot concerné par l'achat. Werte bezogen auf das natürliche Produktfinish und in anerkannten externen Labors geprüft, im Unternehmen erhältlich; für eventuelle Prüfungen der zu erwerbenden Warenposten stehen wir gern zur Verfügung. Значения, касающиеся натуральных характеристик изделий и тестов, выполненных внешними авторизованными лабораториями, имеются компании. Мы готовы выполнить проверку партии товара, которую намереваетесь приобрести.

*** Dato riferito ai formati 60x60, 80x80 e 120x120 cm. Detail referred to the 60x60, 80x80 and 120x120 cm sizes. Donnée se rapportant aux formats 60x60, 80x80 et 120x120 cm. Auf die Formaten 60x60, 80x80 und 120x120 cm bezogen. Данные относятся к форматам 60x60, 80x80 и 120x120 см.

● Per prodotti chimici di uso domestico e additivi per piscina. For domestic chemicals and swimming pool additives. Pour produits chimiques à usage domestique et additifs pour piscines. Für chemische Produkte für den Hausgebrauch und Schwimmbadzusätze. Для бытовых химикатов и добавок для бассейнов.

▲ Valori wet DCOF specifici disponibili in azienda. Wet DCOF specific values available at the company. Valeurs wet DCOF spécifiques disponibles à l'usine. Prüfwerte Wet DCOF stehen im Werk zur Verfügung. Показатели wet DCOF доступны при запросе.

Le tonalità dei campioni sono da considerarsi puramente indicative. - Tones of samples are indicative. - Les tonalités des echantillons sont purement indicatives. Die farbtöne der Muster sind als rein indicativ zu betrachten. - Тона образцов ориентировочные.